

Tested For: Rahul Amin
Smooth-On, Inc.
5600 Lower Macungie Road
Macungie, PA 18062
USA

Phone: (610) 252-5800
Fax:
Mobile:
PO#: 1216LRA
Email: rahul@smooth-on.com

Received: 7/28/2021
Completed: 7/29/2021
Code: F
Test Report: 3-44631-0

Key Test: ASTM E84 (Int Fin)

805

CERTIFICATION: I certify that the reported results were obtained after testing specimens in accordance with the procedures and equipment specified above.



AUTHORIZED SIGNATURE
SGS NORTH AMERICA
/jab

Jillian Guillem

Test Engineer: Jimmy Rosinsky

JUL 30 2021

Enclosure: Graphs

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.

Test Method	: ASTM E84
Test Report #	: 3-44631-0-F
Date	: 7/29/2021
Client	: Smooth-On, Inc.
Operator	: Jimmy Rosinsky
Details of Preparation	: The test specimen was rigid enough to be self-supporting when placed into test position. No additional support was required. The 24 ft. length was comprised of six 4 ft. sections butted end to end.
Observations	: No unusual observations

Area Under Flame Curve (ft min)	: 0.00
Raw Flame Spread Index (ft min)	: 0.00
Rounded Flame Spread Index (ft min)	: 0
Ignition Time	: 06:32 mm:ss
Area Under Smoke Curve (%A min)	: 0.03
Raw Smoke-Developed Index	: 0.03
Rounded Smoke-Developed Index	: 0
Total Gas Flow(L)	: 1598.7
Total Gas Flow(ft ³)	: 56.5
Maximum Flame Front Achieved(ft)	: 0 (@0s)

