## Vertical Burning Test - UL 94, Section 8

Customer: Smooth-On Inc.

Microtek Job No.: 39316 Set No.: 1

SOLDER LIMITS

Temp/Time: N/Asec @ N/A°C

Material: Urethane 98-290 / TASK 7

ANSI: N/A Color: WT

Coating: N/A

Nom. Sample Thk.: As-Measured

Avg. Sample Thk.: 3.568 mm

Test Type Original	Sample No.	Sample Thk: (mm)	Afterf t <sub>1</sub> (sec)	lames t <sub>2</sub> (sec)	Afterglow t <sub>3</sub> (sec)	Sum of after flames (t <sub>1</sub> + t <sub>2</sub> ) (sec)	Sum of afterflame and afterglow (t <sub>2</sub> + t <sub>3</sub> ) (sec)	Did samples burn to the clamp?	Did the cotton ignite?
CONDITION A:	1	3.016mm	0.0	0.0	0.0	0.0	0.0	No	No
48 Hours	2	3.476mm	0.0	0.0	0.0	0.0	0.0	No	No
23 ± 2°C	3	3.996mm	0.0	0.0	0.0	0.0	0.0	No	No
50 ± 5% RH	4	3.645mm	0.0	0.0	0.0	0.0	0.0	No	No
And a second control of a reversion of the second control of the s	5	3.625mm	0.0	0.0	0.0	0.0	0.0	No	No
		200	1 (3)		-22		309	3	
CONDITION B:	6	3.004mm	0.0	0.0	0.0	0.0	0.0	No	No
168 Hours	7	3.293mm	0.0	0.0	0.0	0.0	0.0	No	No
70 ± 1°C	8	3.671mm	0.0	0.0	0.0	0.0	0.0	No	No
	9	4.073mm	0.0	0.0	0.0	0.0	0.0	No	No
	10	3.879mm	0.0	0.0	0.0	0.0	0.0	No	No

Test Results: Meets the requirements of UL 94 Section 8 classification V-0

	Material Classifications				
Criteria Conditions	V-0	V-1	V-2		
Afterflame time for indiviudal sample t <sub>1</sub> or t <sub>2</sub>	≤10s	≤30s	≤30s		
Total afterflame time for any condition set ( $t_1$ plus $t_2$ for the five specimens)	≤50s	≤250s	≤250s		
Afterflame plus afterglow time for each individual specimen after the second flame application ( $t_2$ + $t_3$ )	≤30s	≤60s	≤60s		
Afterflame or afterglow of any specimen up to the holding clamp	No	No	No		
Cotton indicator ignitied by flaming particles or drops	No	No	Yes		

Test Results					
Cond A	Cond B				
0.0s	0.0s				
0.0s	0.0s				
0.0s	0.0s				
No	No				
No	No				



## CERTIFICATE OF CONFORMANCE

Microtek Laboratories certifies that the test equipment used complies with the calibration requirements of ANSI/NCSL Z540-1, IPC-QL-653, and ISO/IEC-17025 and that the data contained in this report is accurate within the tolerance limitation of this equipment.

The materials and/or devices furnished on this order have been tested/analyzed/and inspected in accordance with all designated instructions and specifications. Physical reports and supporting records are on file and available for inspection at Microtek Laboratories for a period not less than five years. Tested samples will be stored at Microtek Laboratories for a period not less than two years unless the customer requests the release of the test samples.

All test procedures detailed are complete. If any additional information or clarification of this report is required, please contact us.

Thank you for selecting Microtek Laboratories for your testing requirements.

Report prepared by,

Respectfully submitted,

June S. Shepher.

Josephin Mazariegos Administrative Assistant MICROTEK LABORATORIES

Date: 2010-06-09

Russ Shepherd

Director PCB\PWB Test Programs
MICROTEK LABORATORIES

Date: 2010-06-09