



VytaFlex® Series

Liquid Urethane Rubbers

PRODUCT OVERVIEW

Using Smooth-On's exclusive "V-Polymer®" technology, **VytaFlex®** urethane rubbers offer superior physical and performance properties for casting concrete. **VytaFlex®** urethanes are available in 10A, 20A, 30A, 40A, 50A and 60A Shore hardness's and feature convenient one-to-one by volume mix ratios. Vacuum degassing is not necessary and **VytaFlex®** rubbers cure with negligible shrinkage to a durable rubber that will last in production.

VytaFlex® mold rubbers work especially well for casting pigmented / colored concrete. Molds made with VytaFlex® Series urethanes will render accurate and uniform colored castings.

VytaFlex® mold rubbers can also be used for a variety of applications including making molds for making special effects, toys and prototypes. Vibrant colors can be achieved by adding So-Strong® Color Tints, available from Smooth-On. *Want to cast gypsum or wax?* Our **ReoFlex®** line of urethane rubbers offers better release properties for casting plaster and wax.

TECHNICAL OVERVIEW

	Shore A	Mix Ratio	Color	Spec. Vol.	Spec. Grav.	Mixed Viscosity	Tear (C)	Elong. At Break	Tensile Strength
VytaFlex® 10	10	1:1 pbv	Off-White	27.9	1.00	3,100 cps.	30 pli	1,000 %	160 psi
VytaFlex® 20	20	1:1 pbv	Clear Amber	27.7	1.00	1,000 cps	58 pli	1,000%	200 psi
VytaFlex® 30	30	1:1 pbv	Off-White	27.3	1.02	1,800 cps	78 pli	1,000%	500 psi
VytaFlex® 40	40	1:1 pbv	Off-White	26.9	1.03	2,000 cps	82 pli	660%	522 psi
VytaFlex® 50	50	1:1 pbv	Off-White	26.7	1.04	2,000 cps	102 pli	400%	588 psi
VytaFlex® 60	60	1:1 pbv	Off-White	26.6	1.04	2,000 cps	136 pli	480%	880 psi

~ **Pot Life*** VytaFlex® 10, 20, 30, 40: 30 minutes
 ~ **Pot Life:** VytaFlex® 50, 60: 60 minutes

~ **Cure Time/Demold*:** Overnight / 16 hours

Shrinkage: Negligible

Note: VytaFlex® 10 should be allowed to cure for 24 hours.

*Values measured at room temperature (72°F/23°C).

Start By Preparing Your Model -

Preparation . . . Store and use at room temperature (72°F/23°C). These products have a limited shelf life and should be used as soon as possible. Environmental humidity should be as low as possible. Good ventilation (room size) is essential. Wear safety glasses, long sleeves and rubber gloves to minimize contamination risk.

Some Materials Must Be Sealed . . . Urethanes are adhesive. To prevent adhesion between the rubber and model surface, models made of porous materials (gypsum plasters, concrete, wood, stone, etc.) must be sealed prior to applying a release agent. SuperSeal® (available from Smooth-On) or One Step® are fast drying sealers suitable for sealing porous surfaces without interfering with surface detail. Sonite Wax® or high-grade shellac is suitable for rough contours. A high quality Shellac is suitable for sealing modeling clays that contain sulfur or moisture (water based). Thermoplastics (polystyrene) must also be sealed with shellac or PVA. **In all cases**, the sealing agent should be applied and allowed to completely dry prior to applying a release agent.

Non-Porous Surfaces – metal, glass, hard plastics, sulfur free clays, etc. require only a release agent.

Applying A Release Agent . . . A release agent is necessary to facilitate demolding when casting into or over most surfaces. Use a release agent made specifically for mold making (Universal® Mold Release available from Smooth-On). A liberal coat of release agent should be applied onto all surfaces that will contact the rubber. **~IMPORTANT:** To ensure thorough coverage, lightly brush the release agent with a soft brush over all surfaces of the model. Follow with a light mist coating and let the release agent dry for 30 minutes. **Because no two applications are quite the same, a small test application to determine suitability for your project is recommended if performance of this material is in question.**

Measuring & Mixing . . .

Liquid urethanes are **moisture sensitive** and will absorb atmospheric moisture. Mixing tools and containers should be clean and made of metal or plastic. Materials should be stored and used in a warm environment (72° F / 22° C). **IMPORTANT:** Shelf life of product is drastically reduced after opening. Immediately replacing the lids on both containers after dispensing product will prolong the shelf life of the unused product. **XTEND-IT® Dry Gas Blanket** (available from Smooth-On) will significantly prolong the shelf life of unused liquid urethane products. These products have a limited shelf life and should be used as soon as possible.

Important: Pre-Mix the Part B before using. After dispensing equal amounts of Parts A and B into mixing container, mix thoroughly for at least 3 minutes making sure that you scrape the sides and bottom of the mixing container several times.

If Mixing Large Quantities (16 lbs./7 kgs. or more) at one time, use a mechanical mixer (i.e. Squirrel Mixer or equal) for 3 minutes followed by careful hand mixing for one minute as directed above. Then, pour entire quantity into a new, clean mixing container and do it all over again.

Although this product is formulated to minimize air bubbles in your the cured rubber, vacuum degassing prior to pouring rubber will further reduce entrapped air .

Pouring

Curing

Performance

For best results, pour your mixture in a single spot at the lowest point of the containment field. Let the rubber seek its level up and over the model. **A uniform flow will help minimize entrapped air.** The liquid rubber should level off at least 1/2" (1.3 cm) over the highest point of the model surface.

Curing . . . Allow rubber to cure a minimum of 16 – 24 hours at room temperature (72 F/22 C) before demolding.

VytaFlex® 10 should cure for at least 24 hours before demolding. Cure time can be reduced with mild heat or by adding Smooth-On “Kick-It®” Cure Accelerator. Do not cure rubber where temperature is less than 65 F /18 C.

Post Curing – Optional . . . Following an overnight cure, heating the rubber to 150° F (65° C) for 4 to 8 hours will increase physical properties and performance.

Using The Mold . . . If using as a mold material, a release agent should be applied to the mold before each casting. The type of release agent to use depends on the material being cast. The proper release agent for **wax, liquid rubber or thermosetting materials** (i.e. Smooth-On liquid plastics) is a spray release made specifically for mold making (available from Smooth-On or your distributor). Prior to casting **gypsum plaster materials**, sponge the mold with a soap solution for better plaster flow and easy release. **In & Out® II Concrete Release Concentrate** (available from Smooth-On) is recommended for releasing abrasive materials like **concrete**.

Performance & Storage - Fully cured rubber is tough, durable and will perform if properly used and stored. The physical life of the rubber depends on how you use it.

Safety First!

Safety First!

Safety First!

Safety First!

The Material Safety Data Sheet (MSDS) for this or any Smooth-On product should be read prior to use and is available upon request from Smooth-On. All Smooth-On products are safe to use if directions are read and followed carefully.

Be careful. Part A is a TDI prepolymer. Vapors, which can be significant if material is heated or sprayed, cause lung damage and sensitization. Use only with adequate ventilation. Contact with skin and eyes may cause severe irritation. Flush eyes with water for 15 minutes and seek immediate medical attention. Remove from skin with waterless hand cleaner followed by soap and water. Prepolymers contain trace amounts of TDI which, if ingested, must be considered a potential carcinogen. Refer to MSDS .

Part B) is irritating to the eyes and skin. If contaminated, flush eyes with water for 15 minutes and seek immediate medical attention. Remove from skin with soap and water. When mixing with Part A follow precautions for handling isocyanates. **Important:** The information contained in this bulletin is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained from the use thereof, or that any such use will not infringe upon a patent. User shall determine the suitability of the product for the intended application and assume all risk and liability whatsoever in connection therewith.

For Technical Help: Tel. (800) 762-0744 Fax. (610) 252-6200 Website: www.smooth-on.com

041908