

# Ease Release™ 2910

**Superior Release For Polyurethane With Excellent Gloss**

**Mann**  
RELEASE TECHNOLOGIES™  
www.smooth-on.com

## PRODUCT OVERVIEW

Ease Release™ 2910 is a superior release agent for casting complex designs using polyurethane elastomers. Ease Release™ 2910 is a heavy-duty silicone based product in a solvent carrier that gives a high gloss surface finish on the molded parts. This product also releases compression molded Thiokol rubbers, EPDM and other synthetic elastomers. Ease Release™ 2910 release agent works on aluminum, chrome, epoxy, and polyurethane molds.

## PROCESSING RECOMMENDATIONS

### Features:

- Easy to apply
- Fast drying
- Effective over a broad temperature range from 70°F to 500°F

### Provides:

- Excellent release
- Excellent surface finish
- Precise duplication of mold details
- Less mold maintenance and down time
- Greater Productivity

Ease Release	Weight/ Gallon	Solvent Carrier	Drying Rate	Flammable	Wetting Quality
2910 Aerosol	N/A	DichloroMonofluoroethane DimethylMethane Butane	Very Fast	No	Excellent
2910-5	6.0#	Petroleum Hydrocarbons	Fast	Yes	Excellent
2910-7	6.4#	Petroleum Hydrocarbons	Slow	Combust.	Good

## PREPARATION AND APPLICATION...

**CONTENTS FLAMMABLE:** Keep product away from flame and all ignition sources. Use this product in a properly ventilated area with at least room size ventilation. Wear safety glasses, long sleeves and rubber gloves to minimize contamination risk. **Store and use material at room temperature (73°F/23°C).**

Thoroughly clean your mold with Mold Cleaner™ 2508 or any suitable cleaner to remove all traces of previous coatings and oils.

Apply Ease Release™ 2910 using aerosol spray or spray equipment for bulk grades. Hold the can (or spray gun) 6 to 8 inches from the mold surface to ensure a light, even coating. When the molds are new or have been blasted with an abrasive, "season" the mold by applying a heavy coating of release. Heat the mold to process temperature, then wipe the excess with a rag, and reapply a light coating of Ease Release™ 2910 before a regular molding.

Ease Release™ 2910 is fast drying and requires no baking during the normal molding process.

Reapply a light coating before each molding.

**Because no two applications are quite the same, a small test application to determine suitability is recommended if performance of this material is in question.**

**Finishing** - Parts molded with Ease Release 2910 must be sanded or machined to remove the shiny surface before painting or bonding.

There are better ways to address the issue of "Painting a Finished Casting" and still gain the benefits of using a mold release. Visit [www.smooth-on.com](http://www.smooth-on.com) and visit our FAQ section under "Casting" to learn how.

### **Safety First!**

The material safety data sheet (MSDS) for this or any Smooth-On product should be read before using and is available on request. All Smooth-On products are safe to use if directions are read and followed carefully.

**Be careful.**

Ease Release™ 300 AEROSOL - CONTENTS UNDER PRESSURE. FLAMMABLE: Keep product away from heat, sparks, flames or open flame. Do not puncture, or incinerate container. Do not expose to heat or store at temperatures above 120°F/48°C. Use only with adequate ventilation.

Ease Release™ 305 and 307 LIQUID - FLAMMABLE: Keep product away from flame and all ignition sources. Use this product in a properly ventilated area with at least room size ventilation.

**First Aid:** If swallowed, do not induce vomiting. Call physician immediately. If overcome by vapors, remove person from contaminated area. Do not give epinephrine. For eye contact, flush eyes thoroughly with water for 15 minutes. For skin contact, wash thoroughly with warm soapy water.

**Note:** Inhalation of high concentrations of vapor can cause central nervous system depression and/or heart irregularities. May generate toxic gases on contact with open flame. EYE IRRITANT. Wear eye protection. Avoid contact with eyes and prolonged or repeated contact with skin. Use only as directed. Keep out of reach of children.

**IMPORTANT** - The information contained in this bulletin is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained from the use thereof, or that any such use will not infringe a copyright or patent. User shall determine suitability of the product for the intended application and assume all associated risks and liability.



**Call Us Anytime With Questions About Your Application.**

**Toll-free: (800) 381-1733 Fax: (610) 252-6200**

[www.smooth-on.com](http://www.smooth-on.com) is loaded with information about mold making, casting and more.