

Epsilon™ PRO

Impact Resistant EPS Foam Coating



www.smooth-on.com

PRODUCT OVERVIEW

Epsilon™ PRO is a thixotropic epoxy coating that self-thickens for brushing onto a variety of surfaces. Compared to original Epsilon™, Epsilon™ PRO offers a longer working time and cured epoxy is semi-rigid, offering better impact resistance. Mix ratio for Epsilon™ PRO is 2A:1B by volume (100A:44B by weight). A gram scale is not needed to use this product.

Applied in thin layers, mixed material holds a vertical surface without sagging or slumping. Material wets out uniformly over different surfaces. Pot life is 22 minutes, with a re-coat time of 3 hours. All layers should be allowed to cure for 16 hours at 73° F / 23° C and can be accelerated with mild heat. Epsilon™ PRO is clear and can be easily colored using SO-Strong™, Ignite™ or UVO™ colorants. Cured coating has a gloss finish and can be sanded, primed and painted.

Applications: Epsilon™ PRO is suitable for use as a protective, impact resistant coating for EPS or polyurethane foam. It can also be applied to plaster, concrete, wood and fabrics. This product is not sensitive to moisture / humidity and contains no

PROCESSING RECOMMENDATIONS

Preparation – Avoid breathing fumes - use in a well ventilated area at minimum. NIOSH approved respirator is recommended. Wear safety glasses, long sleeves and rubber gloves to minimize skin contact. This material has a high exotherm (generates heat). Do not mix components in glass or foam containers.

Materials should be stored and used in a room temperature environment (73°F/23°C). Elevated temperatures will reduce Pot Life. Epsilon™ PRO Part A resin and Part B Hardener must be properly measured and thoroughly mixed to achieve full, high-strength, solid-cure properties. Mixing sticks should be flat and stiff with defined edges for scraping the sides and bottom of your mixing container. **Because no two applications are quite the same, a small test application to determine suitability for your project is recommended if performance of this material is in question.**

Applying a Release Agent – For releasing epoxy from non-porous surfaces such as resin, metal, glass etc., use Ease Release™ 200 or 205 (available from Smooth-On) to prevent adhesion.

Measuring and Dispensing – Stir or shake Part A and Part B thoroughly before dispensing. Accurate ratio measurements by weight are required for the material to cure properly and develop full physical properties. Dispense proper proportions of parts A and B into clean plastic, metal or wax-free paper containers.

Material Properties	
Mix Ratio By Volume	2A:1B
Mix Ratio By Weight	100A:44B
Mixed Viscosity - CPS. (ASTM D2393)	4000
Specific Gravity - Mixed; g./c.c. (ASTM D1475)	1.11
Spec. Volume - Mixed; cu. in./lb. (ASTM D792)	25.0
Pot Life - Minutes (ASTM D2471)*	22
Thin Film Working Time - Minutes*	35
Thin Film Tacky Recoat Time - Hours*	3
Thin Film Tack Free Time - Hours	4
Cure Time - Hours*	16
Color - Mixed	Clear Amber
Shore D Hardness (ASTM D2240)**	65D
* Dependant on mass ** Value measured after 7 days at 73°F / 23°C	

Epsilon™ PRO Coverage Rates	
Amount	Applied at 1/16" (1.6mm)
Trial Unit (1.44 lbs. / 0.65 kg)	4.0 ft ² (0.37 m ²)
Gallon Unit (11.52 lbs. / 5.23 kg)	32.0 ft ² (2.97 m ²)
5 Gallon Unit (64.8 lbs. / 29.39 kg)	180 ft ² (16.7 m ²)

Mixing – **Do not use foam or glass mixing containers.** Be sure mixing utensils are clean and free of any potential contaminants such as dirt, dust or grease. Mix Parts A and B thoroughly for at least 3 minutes with a square edged mixing stick. Be aggressive and scrape sides and bottom of mixing container several times. Use the square edge of mixing stick to bring material off of the sides of container and blend. **If using a drill mixer**, follow with hand mixing as directed above to ensure thorough mixing. **NOTE:** Pot life can be extended by pouring mixture into a shallow pan, reducing its mass.

Important - Mixed Epsilon™ PRO Resin with PART B Hardener is exothermic, meaning it generates heat. A concentrated mass of mixed epoxy in a confined area such as a mixing container can generate enough heat to melt a plastic cup, burn skin or ignite combustible materials if left to stand for its full Pot Life. If a batch of mixed epoxy begins to exotherm, move it outdoors to an open air environment.

Safety First!

The material safety data sheet (MSDS) for this or any Smooth-On product should be read before using and is available on request. All Smooth-On products are safe to use if directions are read and followed carefully.

Epsilon™ PRO Resin PART A:

WARNING: IRRITANT TO EYES, SKIN & MUCOUS MEMBRANES.

Epsilon™ PRO Resin is irritating to the eyes and skin. Avoid prolonged or repeated skin contact to prevent possible sensitization. Avoid breathing vapors and use only with adequate ventilation. Wear personal protective equipment.

First Aid: In case of eye contact, flush thoroughly with water for 15 minutes and get immediate medical attention. In case of skin contact, wipe clean with white vinegar and wash thoroughly with soap and water. If irritation persists, get medical attention. If swallowed, do not induce vomiting. Drink 1 - 2 glasses of water and get immediate medical attention. If vapors are inhaled or if breathing becomes difficult, remove person to fresh air. If symptoms persist, get medical attention.

Keep Out Of Reach Of Children.

Epsilon™ PRO PART B Hardener:

WARNING: IRRITANT TO EYES, SKIN & MUCOUS MEMBRANES.

Epsilon™ Hardener is a corrosive material and can cause severe eye and skin burns. It is a sensitizer that may cause dermatitis from skin contact or vapor inhalation. Use this product only with adequate ventilation. Remove contaminated clothing and wash from skin with soap and water.

First Aid: In case of eye contact, flush thoroughly with water for 15 minutes and get immediate medical attention.

Keep Out Of Reach Of Children.

IMPORTANT: The information contained in this bulletin is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained from the use thereof, or that any such use will not infringe upon a patent. User shall determine the suitability of the product for the intended application and assume all risk and liability whatsoever in connection therewith.

Adding Color - Epsilon™ PRO Epoxy Surface Coat System can be colored with UVO™ or IGNITE™ colorants (from Smooth-On). Pre-mix colorant with Part A thoroughly and then add Part B.

Thickening Epsilon™ PRO - Adding Ure-fil™ 9 (fumed silica) to Epsilon™ PRO creates a creamy, easy to spread and smooth paste which is perfect for filling seams, repairing small dents & divots in foam or smoothing rough areas on EPS foam surfaces. Adding Ure-fil™ 11 (short strand fibers) will yield a slightly thicker paste for better vertical surface hold-ability. Mixture can be used to build up surfaces quickly or to add texture. Also good for filling larger holes or areas that need reinforcement. Recommended: start with a mix ratio of 2 Parts A to 2 Parts Filler to 1 Part B. The amount of filler can be increased or decreased based on application requirements.

Extending Working Time – mixed material in a deep mixing cup or bucket will set up quickly due to concentration of the liquid mass. Pour mixture into a flat (shallow) metal cookie sheet or baking pan and dispense product from there. Working time will be extended.

Apply In Thin Layers - two thin layers of Epsilon™ PRO are recommended for a smooth, uniform coating. Using chip brush or roller, apply 1st thin layer to surface and let epoxy partially cure until “tacky hard”. Apply 2nd thin layer. Allow both layers to fully cure.

Important: minimum recommended thickness: 1/16” (0.16 cm). Do not apply epoxy thicker than 1/8” (0.32 cm) per layer as this may cause sagging and result in an uneven cured coating.

When coating areas of fine detail, using successive thin layers of Epsilon™ PRO will allow a protective layer of material to be built up without obscuring the detail of the original surface.

Cure Time: Refer to the specified “*Cure Times*” in the “*Material Properties*” section on front of this Technical Bulletin. Fully cured material will be hard and unable to penetrate with a finger nail. Cured epoxy can now be dry sanded.

If machining or sanding, wear NIOSH approved mask to prevent inhalation of particles.

Curing - This product will cure at room temperature (73°F/23°C) and does not require heat.

Painting – Epsilon™ PRO can be painted and/or primed and then painted with acrylic enamel paints. Let paint fully dry before putting part into service. For best results, lightly sand surface prior to painting.

Removing Epoxy – Uncured / Non-curing epoxy: Scrape as much material as possible from the surface using a scraper. Clean the residue with E-POX-EE KLEENER™ available from Smooth-On, lacquer thinner, acetone or alcohol. Follow safety warnings pertaining to solvents and provide adequate ventilation.



Call Us Anytime With Questions About Your Application

Toll-free: (800) 381-1733 Fax: (610) 252-6200

The new www.smooth-on.com is loaded with information about mold making, casting and more.