

# POLYBAC #1183-WB

## CERAMIC BEADED WEARING COMPOUND

Data Sheet M-014

### 1. PRODUCT NAME

POLYBAC #1183-WB

### 2. MANUFACTURER

Polygem, Inc.  
1105 Carolina Drive  
West Chicago, IL 60185  
Telephone: (630) 231-5600  
FAX: (630) 231-5604  
Internet: www.polygem.com

### 3. PRODUCT DESCRIPTION

POLYBAC #1183-WB is a specially formulated epoxy paste blended with abrasion resistant small black ceramic beads to provide a durable barrier to protect surfaces subjected to wear and abrasion. POLYBAC #1183-WB is an easy to mix 1 to 1 by volume ratio. POLYBAC #1183-WB is waterproof and resistant to most chemicals and solvents. POLYBAC #1183-WB is a thick non-sag paste compound that will allow for vertical and overhead patching.

#### Advantages

- Extremely durable ceramic matrix.
- Chemical Resistant
- No VOC's or Solvents
- Low Odor Formula
- Bonds to most dry surfaces

#### Uses

For the patching and repair of worn metal or concrete surfaces that are exposed to abrasive environments. POLYBAC #1183-WB is ideal for use on:

- Pipe Elbows
- Vibrating Screens & Beams
- Cyclones
- Hopper and Chutes
- Pump Casings
- Wear Plates
- Brick Corners and Transitions Areas
- Dust Collection Systems
- Chipper and Grain Bins
- Pneumatic Conveyors
- Heat Exchangers and Tube Sheets
- Augers, Fan and Impeller Blades

### 4. APPLICATION INSTRUCTIONS

- 1) Clean surface by sandblasting or grinding to provide rough white-metal profile.
- 2) Thoroughly mix equal amounts by volume of Part A Resin with Part B Hardener until streak free. Mix only enough that can be applied in 35 minutes.

- 3) Spread mixed epoxy with trowel or putty knife and worked well into the surface.
- 4) Epoxy may be smoothed with a trowel dipped in a solvent.

#### Packaging

POLYBAC #1183-WB is available in 2 kit sizes: 7 lb. - 2 Quart Kits and 30 lb. - 2 Gallon Kits.

#### Shelf Life

Factory sealed containers of this product are guaranteed to be of first quality for min. 12 months.

#### Limitations

- Do not apply over 5/8" thick per layer. Additional thickness can be built up with multiple coats. Allow prior coat to harden and cool to touch before the application of the next layer.
- Not for use on wet or oily surfaces.
- Do not install when surface temperature is below 45°F (7°C) or above 90°F (32°C).
- During cool conditions epoxy will cure slower, protect finished work from wear and abrasion until fully cured.

#### Cautions

- Wear chemical goggles and NIOSH approved respirator. Wear proper protective clothing and gloves to prevent direct contact of resins. Consult Material Safety Data Sheet for full listing protective requirements.
- POLYBAC #1183-WB may irritate eyes and skin. Avoid contact with eyes or prolonged contact with skin.
- For professional use only.
- Keep out of reach of children.

### 5. TECHNICAL DATA

Performance Properties  
Test/Test Method Results

Pot Life @ 77°F (100 gms)	35 mins.
Compressive ASTM D-695	10,600 psi
Compressive Modulus	308,000 psi
Tensile Strength ASTM D-638	8,300 psi
Elongation ASTM D-638	3% min.
Bond Strength ASTM C-882	2,000 psi
Shore D Hardness	85-80
Cure Time @75 F	16-24 hours
Mix ratio by volume	A/B 1:1
Mixed Viscosity	Heavy Paste
Color Mixed	Gray

Polygem, Inc. warrants its products to be free of manufacturing defects and that, at the time and place of shipment, our material will meet current physical properties when applied within Polygem's directions and tested in accordance with ASTM and Polygem standards. Polygem, Inc.'s liability is limited to replacement of material found defective. As Polygem, Inc. has no control over the use to which others may put its products, it is recommended that the product be tested to determine if suitable for a specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Nothing contained herein shall be construed to be a recommendation to use or as a license to operate under or to infringe any existing patents.

POLYBAC #1183-WB.doc/Rev. 9/5/03

Data sheets are subject to change without notice, for latest revision check our website at www.polygem.com