

737- 738 & 739 WATER BASED URETHANES

ALIPHATIC POLYURETHANE TOPCOAT & SEALER

1. PRODUCT NAME

737 - SATIN
738 - GLOSS
739 - MATTE

2. MANUFACTURER

Polygem, Inc.
1105 Carolina Drive
West Chicago, IL 60185
Telephone: (630) 231-5600
FAX: (630) 231-5604
www.polygem.com

3. PRODUCT DESCRIPTION

737, 738 & 739 WB Urethane is an aliphatic two component water-based topcoat. It provides a tough durable surface that exhibits a high gloss, flat matte or when 738 and 739 are blended 1:1 satin finish. Lasts significantly longer than acrylic sealers.

Advantages

- Non- yellowing, high gloss
- No Odor
- VOC compliant
- Easily Applied
- Long Wear Resistance
- Provides glossy, "wet" look

Uses

Horizontal Surfaces such as: Epoxy Flooring Topcoat, Showrooms, Decorative Concrete, Garages, Stamped Concrete, Exposed aggregate

4. APPLICATION INSTRUCTIONS

1. Apply to a structurally sound, free of dust, dirt, mortar residue, curing and form release compounds and all other contaminants.
2. At time of use the Part A should be blended with Part B with slow agitation for 1-2 minutes. Use a power mixer with a jiffy type mixer. The A/B mixture will slightly thicken after blending. Allow the mix to stand for 5-10 minutes before use. Do not thin or dilute.
3. Apply WB Urethane in a uniform, continuous film by squeegee, airless sprayer, short napped mohair roller, foam applicator, lamb's wool applicator or paint brush. Use a lamb's wool applicator or roller to pick up puddles or excess material.
4. Application to epoxy flooring should be done after the epoxy is tack free and no longer than 24 hours.

5. A primer is required for application of WB Urethane to concrete or masonry surfaces. Apply WB urethane after the primer is dry and not longer than 24 hours.

Packaging

1 Gallon Kits

Shelf Life

Unopened containers are guaranteed for 1 year.
Store in temperatures between 60°-80° F.
Storing above 85° will reduce shelf life.
Keep from freezing

Limitations

Do not apply to exterior surfaces if rain is expected within 12 hours after application or in direct sunlight at ambient temperatures more than 90 degrees F. Do not apply to frozen or frost surfaces. Not recommended for asphalt surfaces- always apply a test area.

Cautions

Wear chemical goggles and NIOSH approved respirator. Wear proper protective clothing and gloves to prevent direct contact of resins. Consult Safety Data Sheet for full listing protective requirements.

737, 738 & 739 may irritate eyes and skin. Avoid contact with eyes or prolonged contact with skin.

For professional use only.
Keep out of reach of children.

5. TECHNICAL DATA

Performance Properties @ 75F., 50% R.H.
Test/Test Method Results

Viscosity, cps	220-380
Color	
Wet	Milky White
Dry	Crystal Clear
Pot Life, hours	2-3
Dry time, hours	
Set to Touch	2
Surface Dry	3
Hard Dry	5
% Solids, by weight	56
Volatile Organic Content, g/1	<25
Tire Marking Resistance	Excellent
Coverage rate, sq. ft./gal	250-350

Polygem, Inc. warrants its products to be free of manufacturing defects and that, at the time and place of shipment, our material will meet current physical properties when applied within Polygem's directions and tested in accordance with ASTM and Polygem standards. Polygem, Inc.'s liability is limited to replacement of material found defective. As Polygem, Inc. has no control over the use to which others may put its products, it is recommended that the product be tested to determine if suitable for a specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Nothing contained herein shall be construed to be a recommendation to use or as a license to operate under or to infringe any existing patents.